



LOW VOC MACTEK

R.J. McGlennon Co. Inc.
198 Utah Street
San Francisco, CA 94103

Product Data Sheet

Phone (415) 552-0311
Fax (415) 552-8055

42 SERIES U-200 GRAY LOW VOC PRIMER

Description Fast drying, high solids low VOC rust inhibitive modified alkyd primer for use on steel surfaces. This very low VOC primer is lead and chromate free and will dry to touch in 30 minutes: with dry to handle in 1 to 2 hours (under standard conditions at 1 mil dry film thickness).

↓	Specifications	Weight per Gallon:	10.63	Coating VOC:	340 G/L 2.83 Lb/Gal
		Solids by Weight %:	60.94	Material VOC:	227 G/L 1.89 Lb/Gal
		Solids by Volume %:	40.68	VOC Weight Ratio =	0.29 LbVOC/Lb Solid
		Coverage @ 1 mil:	652 SqFt./Gal.		
		Viscosity:	800 - 1100 CPS (#3/60)	Gloss:	Flat

Surface Preparation Surfaces must be commercially clean and free of dirt, grease and water. Remove any rust deposits. Any existing coatings should be checked for integrity and compatibility and sanded for adhesion and appearance.
No Maclac paint product has ever contained any lead. But if you are preparing previously painted surfaces with unknown paints please observe the following precautions. Warning! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NOISH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Mixing & Thinning Product as supplied is ready to spray. If any thinning is required, then we recommend thinning with Acetone, as this will not change the VOC content. Additional thinning with a non-exempt thinner will raise the VOC content. Thoroughly mix the material by stirring or shaking prior to application.

Application & Dry This primer is designed for spray application only. It may be applied with conventional, airless, air-assist airless or HVLP spray equipment. U-200 will dry to touch within 20 minutes and to handle in about 1 hour when applied to approximately 1 mil dry film thickness. This primer is lift-resistant, and may be topcoated with enamels, lacquers, epoxies, urethanes, and DTM waterborne coatings.

Performance & Durability Passes 200 hours Salt Spray testing as per ASTM B-117 when applied to 2 - 3 mils. on phosphate treated panels. Tape test adhesion to steel as per ASTM D3359-78: passes 4B to 5B. U-200 is ideal for corrosion and weather resistant requirements.

Environmental & Safe Handling Maximum Coating VOC content as supplied is 340 G/L (2.83 Lbs/Gal.) Warning: flammable mixture. Do not use near heat, sparks, flames, or any ignition sources. Do not cut empty containers. Use only with adequate ventilation. Dispose of any product only in accordance with all applicable regulations. See product material safety data sheet titled "42MSD - Mactek Low VOC High Solids Primers" for full details.

LIMITED WARRANTY

The information contained herein is offered to assist customers in determining whether our products are suitable for their applications. We request that customers examine our products before use and satisfy themselves as to their suitability. We warrant that our products will meet our written specifications. Since application circumstances, substrate condition and product intermix are beyond our control, we cannot guarantee results under all possible situations. R.J. McGlennon Co. Inc. makes no representation as to the results the user will achieve.
Technical advice furnished by seller or any seller's agents shall not constitute a warranty. Any liability arising out of any condition resulting from the use of any R.J. McGlennon Co. Inc. product shall be limited to replacement of such product.